

PRODUCT DESCRIPTION :

Superflor is a self levelling flooring, a mixed that can be spread with a V-notched squeegee or trowel. These system are the answer for both new construction and renovated areas, and can be installed over most sound floors. When cured, produces a dense non porous floor that is chemical and dirt resistance.

RECOMMENDED USE :

Flooring , Beverage processing , Cleaning room , Food preparation , chemical processing, Warehouses etc.

PHYSICAL DATA :

Colour	According to colour card	
Volume Solid (%)	100	(ASTM D2697 Modified)
Specific gravity	1.25-1.30 (part A)	Drying time @ 25 deg C
	1.43-1.45 (mixed)	Dry to touch 4-5 hours
Gloss	Glossy	Dry to hard 10-12 hours
Surface	Concrete	Cured to hard 2-7 days
Flash point	80 $\pm$ 2 deg C	-Recommended film thickness
Film thickness recommended	3000 microns	-Good ventilation
Theoretical coverage	4.6 sq. m / Set (A+B+C)	-Dependent on temperature and humidity

APPLICATION DATA :

Application method	Trowel with putty knife and V-notch squeegee
Mix (by weight)	9.5 part of part A , 4.2 part of part B and 6.3 part of part C
Potlife	30 minutes @ 25 deg C
Cleaner	Thinner 4K No. 65

SURFACE PREPARATION :

Surface must be clean, Remove all dirt , grease and other foreign matter by cleaner and sandblasting , or mechanical abrasion . Remove water and dust from the surfaces.

RECOMMENDED SYSTEM :

Superguard sealer
Superflor

STORAGE AND HANDLING :

Storage	The product must be stored in well ventilated place protected from high temperature. Container must be kept tightly closed .
Handling	Handle with care . Stir well before use .
Packing	part A = 9.5 kg , part B = 4.2 kg , part C = 6.3 kg

HEALTH AND SAFETY :

Avoid contact with skin and eyes wear . Wear suitable protective clothing such as overalls during painting.
Avoid skin contact . Spillage on skin should immediately be removed with soap and water.
Eyes should be flushed with water and medical attention sought immediately.